



EUCO QWIKJOINT UVR

UV-RESISTANT POLYUREA FLOOR JOINT FILLER

EUCLID CHEMICAL

PACKAGING

10 gal (37.9 L) unit

Code: 692NB 10 (Neutral Base)

Code: 693HP 10 (Standard Gray)

Code: 692S 10 (Colors)

22 oz cartridge (650 mL), case of 12

Code: 692S 94 (Colors)

APPROXIMATE COVERAGE

1 gallon (3.79 L) of EUCO QWIKjoint UVR yields 231 in³ (3785 cm³) of material.

One 22 oz (650 mL) cartridge yields 40 in³ (655 cm³) of material. 6 cartridges equal approximately 1 gallon of material.

CLEAN UP

EUCO SOLVENT or acetone may be used for clean-up of tools and equipment. Clean excess material before EUCO QWIKjoint UVR has cured. Cured material will require removal by mechanical means.

SHELF LIFE

1 year in original, unopened package

SPECIFICATIONS AND COMPLIANCES

- Complies with ACI 302 performance recommendations regarding control and construction joint fillers.
- USGBC LEED Version 4, BD&C, ID&C
- The WELL Building Standard
- ANSI/GBI 01, Green Building Assessment Protocol
- Acceptable for use in USDA/FDA inspected facilities

DESCRIPTION

EUCO QWIKjoint UVR represents a new generation of polyurea technology with features and benefits unlike any other polyurea joint filler on the market. EUCO QWIKjoint UVR resists fading from ultraviolet light greater than any existing product. It is a fast-setting, semi-rigid polyurea, primarily used for filling construction and control joints in industrial and commercial concrete floors. EUCO QWIKjoint UVR can be shaved flush with the floor shortly after placement or up to 24 hours later. EUCO QWIKjoint UVR supports and protects joint edges from heavy loads and wheel traffic, reducing spalling of the joint edges. EUCO QWIKjoint UVR is available in 33 standard colors and in a Neutral Base, that can be colored on site with EUCLID UNIVERSAL COLOR PACKS; available in the same 33 colors.

PRODUCT CHARACTERISTICS

FEATURES/BENEFITS

- Unparalleled UV resistance
- Fast setting formula reduces downtime
- Large shave-time window allows for greater flexibility in scheduling joint filling operations
- Tough performance reduces floor joint repairs and maintenance
- Will cure in temperatures as low as -20 °F (-29 °C)
- No bubbles/foaming when used in damp joints
- Less moisture-sensitive than standard polyureas
- Available in 33 standard colors

PRIMARY APPLICATIONS

- Concrete construction & control joints
- Crack and joint repair for old floors
- Industrial and commercial floors
- Freezer floors

APPEARANCE

EUCO QWIKjoint UVR is available in 33 standard colors and in a Neutral Base that can be colored on site using EUCLID UNIVERSAL COLOR PACKS, which are available in the same 33 standard colors. See the EUCLID UNIVERSAL COLOR CHART for available colors. The user should expect some batch to batch variability in color. If possible, "box" the Part B after pre-stirring each pail to ensure color uniformity.

COVERAGE

The following table gives rough guidelines on estimating the amount of material needed. These numbers represent the length of joint that can be filled with 1 gallon (3.79 L) of material, based on the joints' width and depth.

	Joint Depth				
Joint Width	1"	1.5"	2"	2.5"	3"
3/32" (2.4 mm)	205 ft (62.5 m)	136 ft (41.5 m)	102 ft (31.1 m)	82 ft (25.0 m)	68 ft (20.7 m)
1/8" (3.2 mm)	154 ft (46.9 m)	102 ft (31.1 m)	77 ft (23.5 m)	61 ft (18.6 m)	51 ft (15.5 m)
3/16" (4.8 mm)	102 ft (31.1 m)	68 ft (20.7 m)	51 ft (15.5 m)	41 ft (12.5 m)	34 ft (10.4 m)
1/4" (6.4 mm)	77 ft (23.5 m)	51 ft (15.5 m)	38 ft (11.6 m)	30 ft (9.1 m)	25 ft (7.6 m)
3/8" (9.5 mm)	51 ft (15.5 m)	34 ft (10.4 m)	25 ft (7.6 m)	20 ft (6.1 m)	17 ft (5.2 m)
1/2" (12.7 mm)	38 ft (11.6 m)	25 ft (7.6 m)	19 ft (5.8 m)	15 ft (4.6 m)	12 ft (3.7 m)

TECHNICAL INFORMATION

The following are typical values obtained under laboratory conditions. Expect reasonable variation under field conditions.

Test Method	Test Property	Values
-	Gel Time	25 to 30 seconds
ASTM D2240	Shore D Hardness	34 to 36
ASTM D2240	Shore A Hardness	84 to 88
ASTM D412	Tensile Strength @ 7 days	660 psi (4.6 MPa)
ASTM D412	Elongation @ 7 days	220% to 260%
-	Shave "Window"	1 to 24 hours
-	Tack-Free Time	3 to 4 minutes
-	Traffic Ready Time	Light Traffic: 1 hour Heavy Traffic: 2 hours
ASTM D4541	Adhesion to Concrete @ 7 days	250 psi (1.7 MPa)
ASTM D2196	Viscosity	Part A: 2,000 cp Part B: 1,800 cp
-	Mix Ratio	1:1

Chemical Resistance ASTM D1308	
Acetic Acid, 10%	No effect
Alcohol, 10%	No effect
Ammonium Hydroxide, 10%	No effect
Brake Fluid	Swelled, softened
Diesel Fuel	Discolored
Ethylene Glycol (antifreeze)	No effect
Gasoline	Stained
Hydrochloric Acid, 20%	Slight swelling
JP-4 Jet Fuel	No effect
Used Motor Oil	Stained
Salt Water	No effect
Sodium Hydroxide, 10%	Slightly discolored
Sulfuric Acid, 10%	No effect
Xylene	No effect

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.

DIRECTIONS FOR USE

Surface Preparation: All joints to be filled must be clean and dry. All oil, dirt, debris, paint and any other material that may be a bond breaker must be removed. The final step in cleaning must be the complete removal of all residue by use of oil-free compressed air, or by re-cutting the joint, followed by vacuuming. All joint facings must possess an open surface texture with all curing compounds and sealers removed. If this product will be used for filling floor cracks, the cracks must be routed out and cleaned before filling. For proper installation, all edges must be squared off.

Joint Backing: To provide proper load transfer, EUCO QWIKjoint UVR must be filled full depth of the joint or crack. Do not use backer rod or other fill material for the purpose of reducing volume. Dried silica sand, 1/16" to 1/8" (1.5 to 3 mm), may be used to fill the crack at the bottom of the joint to prevent material loss through the slab.

Priming: EUCO QWIKjoint UVR does not require a primer before application.

Preparation of 10 gal (37.9 L) units

Mixing: Due to its extremely fast set time, EUCO QWIKjoint UVR requires machine mixing and placing. ****Slowly pre-mix Part B separately before using with a slow speed drill and mixing paddle for 2 to 3 minutes.** Do not whip air into the Part B while mixing. Follow mechanical pump manufacturer's equipment instructions for operation.

NOTE: If EUCO QWIKjoint UVR is to be stored in the dispensing pump overnight, place a sheet of plastic wrap directly on top of the liquid material in each tank to prevent exposure to air.

Euclid Universal Color Packs: EUCO QWIKjoint UVR Neutral Base can be colored using 1 EUCLID UNIVERSAL COLOR PACK (EUCO Pack) per 10 gal (37.85 L) unit. Prior to mixing the unit together, stir the color pack into the part "B" side of the product while conducting the pre-mix as described above, until it is fully dispersed. EUCLID UNIVERSAL COLOR PACKS are available in 33 standard colors, see EUCLID UNIVERSAL COLOR CHART for available colors.

Preparation of 22 oz (650 mL) cartridges

QWIKjoint UVR cartridges must be shaken well before opening and using, as some settlement is normal during storage. Remove the threaded cartridge nut, then remove the white plastic plug from the top of the cartridge. The nut and plug can be set aside and later used to re-seal a partially used cartridge. To avoid cross contamination during re-sealing, clean the white plastic plug prior to re-inserting in the top of the cartridge. Thread the included static mixing nozzle onto the cartridge securely. Load the cartridge into a 1:1 ratio, dual-component dispensing gun, designed to accommodate 600 mL (300 mL x 300 mL) cartridges. Hold the gun with the mixing nozzle pointing straight upward, and pump EUCO QWIKjoint UVR up to the top of the static mixing nozzle. Then, tilt the gun downward and dispense the first 2 to 3 pumps (or until material appears uniform) of material into a disposable container. Discard this material. The cartridge is now prepared for the placement of EUCO QWIKjoint UVR.

Placement for 10 gal (37.9 L) units and 22 oz (650 mL) cartridges

EUCO QWIKjoint UVR must be installed in the joint full depth. Joints should be slightly overfilled and shaved smoothly with the surrounding joint edges, giving the floor joints a flat appearance. Shaving of excess EUCO QWIKjoint UVR can begin approximately 1 hour after placement, and up to 24 hours later, depending on jobsite conditions such as the concrete and ambient temperatures.

PRECAUTIONS/LIMITATIONS

- **Based on ACI 302 recommendations, joint fillers should be applied as late as possible after construction to allow for minimal additional slab shrinkage. Consult ACI 302 comments regarding concrete shrinkage, joint filling and user expectations.**
- One EUCLID UNIVERSAL COLOR PACK (EUCO Pack) may be added per 10 gal (37.85 L) unit of Neutral Base; mix into the "B" side.
- EUCO QWIKjoint UVR material and all application equipment should be kept at ambient temperatures of 50°F (10°C) or above.
- Surface and ambient temperature during applications should be between -20 °F and 90 °F (-29 °C and 32 °C)
- Do not use EUCO QWIKjoint UVR as an expansion joint sealant.
- Contact surfaces must be clean and dry for best adhesion.
- Joint edges must be thoroughly cleaned prior to filling, particularly if a floor sealer or densifier has been applied.
- Coatings may not adhere to EUCO QWIKjoint UVR. If the floor is intended to receive a seamless epoxy or urethane coating, refer to our "Epoxy & Urethane Coatings Application Guide".
- Product may slightly discolor if constantly exposed to exterior UV radiation.
- In all cases, consult the Safety Data Sheet before use.

Rev. 06.23

WARRANTY: The Euclid Chemical Company ("Euclid") solely and expressly warrants that its products shall be free from defects in materials and workmanship for one (1) year from the date of purchase. Unless authorized in writing by an officer of Euclid, no other representations or statements made by Euclid or its representatives, in writing or orally, shall alter this warranty. EUCLID MAKES NO WARRANTIES, IMPLIED OR OTHERWISE, AS TO THE MERCHANTABILITY OR FITNESS FOR ORDINARY OR PARTICULAR PURPOSES OF ITS PRODUCTS AND EXCLUDES THE SAME. If any Euclid product fails to conform with this warranty, Euclid will replace the product at no cost to Buyer. Replacement of any product shall be the sole and exclusive remedy available and buyer shall have no claim for incidental or consequential damages. Any warranty claim must be made within one (1) year from the date of the claimed breach. Euclid does not authorize anyone on its behalf to make any written or oral statements which in any way alter Euclid's installation information or instructions in its product literature or on its packaging labels. Any installation of Euclid products which fails to conform with such installation information or instructions shall void this warranty. Product demonstrations, if any, are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. Buyer shall be solely responsible for determining the suitability of Euclid's products for the Buyer's intended purposes.