

# MasterSeal® NP 150™

Low-modulus, non-sag, elastomeric, hybrid sealant

FORMERLY SONOLASTIC® 150 VLM

## PACKAGING

- 300 ml (10.1 fl oz) cartridges, 30 cartridges per carton
- 20 oz (590 ml) ProPaks, 20 per carton

## COLORS

White, Stone, Limestone, Black, Medium Bronze, Aluminum Gray, Tan, Off-White, Special Bronze, Precast White

## YIELD

See page 3 for charts

## STORAGE

Store in original, unopened containers in a cool, dry area. Protect unopened containers from heat and direct sunlight. Storing at elevated temperatures will reduce shelf life.

## SHELF LIFE

15 months when properly stored

## VOC CONTENT

13.6 g/L  
less water and exempt solvents

## DESCRIPTION

MasterSeal NP 150 is a high performance, very low-modulus, high-movement, non-sag, fast-curing, hybrid sealant.

## PRODUCT HIGHLIGHTS

- Superior adhesion results in a long-lasting bond, helping to reduce call backs
- Low modulus to accommodate for joint movement (100% extension in EIFS joints with little stress on bond line)
- Can be painted with elastomeric coatings soon after installation
- Easy to gun and tool, speeding up application
- Wide temperature application range
- Weather resistant for long-lasting weathertight seals
- Fast curing helps to speed up jobsite production
- Non-staining formula for use on stone and other sensitive substrates
- Available in ProPaks to reduce jobsite waste and lower disposal costs
- Meets all state and federal VOC regulations
- Can adhere to green concrete in as little as 72 hours after pour
- Adheres to low energy surfaces including polyethylene, polypropylene, and polyolefins

## SUBSTRATES

- EIFS
- Stucco
- Aluminum
- Concrete
- Masonry
- Wood
- Stone
- Metal
- Vinyl
- Fiber cement siding

## APPLICATIONS

- Vertical or horizontal
- Exterior or interior
- Above grade
- Joints with high movement
- In place of silicone sealants
- Store front systems
- Expansion joints
- Panel walls
- Precast units
- Aluminum, vinyl and wood window frames
- Fascia
- Parapets
- Sanitary applications
- Rough opening liquid flashing
- Window setting adhesive bead
- Window flange sealant
- Air infiltration sealant
- Low surface energy (LSE) substrates with MasterSeal P 173 primer
- Perimeter weatherseal
- Transition seam sealant

## HOW TO APPLY

### JOINT PREPARATION

1. The product may be used in sealant joints designed in accordance with SWR Institute's Sealants - The Professional's Guide.
2. In optimal conditions, the depth of the sealant should be ½ the width of the joint. The sealant joint depth (measured at the center) should always fall between the maximum depth of ½" and the minimum depth of ¼". Refer to Table 1.

### Technical Data

#### Composition

MasterSeal NP 150 is a formulation based on hybrid polymer.

#### Compliances

- ASTM C 920, Type S, Grade NS, Class 50, Use NT, M, A, and O\*  
-capable of +100/-50% movement under typical field conditions.
- ASTM C 1382 for use with EIFS wall systems at 100% Extension
- Federal Specification TT-S-001543A, Type II, Class A, Type Nonsag
- Federal Specification TT-S-00230C, Type II, Class A
- Corps of Engineers CRD-C-541, Type II, Class A
- CFI accepted
- USDA compliant for use in areas that handle meat and poultry  
\*Refer to substrates in Where to Use.


#### Typical Properties

PROPERTY	VALUE
Service temperature range, °F (°C)	-40 to 180 (-40 to 82)
Shrinkage	None

### Test Data

PROPERTY	RESULTS	TEST METHOD
<b>Movement capability, %</b>	±50	ASTM C 719
<b>Extension</b>	100%	ASTM C 1382
<b>100% modulus, psi (MPa)</b>	35 (0.24)	ASTM D 412
<b>Tensile strength, psi (MPa)</b>	140–180	ASTM D 412
<b>Tear strength, lb/in (kg/cm)</b>	40 (7.1)	ASTM D 1004
<b>Ultimate elongation at break, %</b>	800–1,000	ASTM D 412
<b>Rheological, (sag in vertical displacement), at 120 °F (49 °C)</b>	No sag	ASTM C 639
<b>Extrudability, sec</b>	2 – 3	ASTM C 1183
<b>Hardness, Shore A, at standard conditions</b>	17	ASTM C 661
<b>Weight loss, after heat aging, %</b>	< 10	ASTM C 1246
<b>Tack-free time, min (maximum 72 hours)</b>	90	ASTM C 1246
<b>Stain and color change</b>	Passes (no visible stain)	ASTM C 510
<b>Bond durability,* pli on aluminum and concrete, +/- 50% movement</b>	Passes	ASTM C 719
<b>Adhesion* in peel, pli (kg/cm), (minimum 5 pli [0.89 kg/cm])</b>		ASTM C 794
Aluminum	35 (6.2)	
Concrete	36 (6.4)	
<b>Artificial weathering, Xenon arc, 2,000 hrs</b>	No Cracking	ASTM G 155

\*Concrete primed with MasterSeal P 179 for water immersion as indicated in ASTM C 920. Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.



**SEALANT-WATERPROOFING & RESTORATION INSTITUTE**

Issued to: Master Builders Solutions Construction Systems, LLC US  
Product: MasterSeal NP 150

**C719: Pass** ✓ Ext:+50% Comp:-50%

**Substrate:** Primed Mortar, Unprimed Aluminum, & Unprimed Glass (mortar substrates were primed with MasterSeal P179)

**Validation Date:** 7/12/21 - 7/11/26

**No. 202113NP150** copyright © 2021

**SEALANT VALIDATION**  
[www.swrionline.org](http://www.swrionline.org)

- In deep joints, the sealant depth must be controlled by closed cell backer rod or soft backer rod. Where the joint depth does not permit the use of backer rod, a bond breaker (polyethylene strip) must be used to prevent three-point bonding.
- To maintain the recommended sealant depth, install backer rod by compressing and rolling it into the joint channel without stretching it

lengthwise. Closed cell backer rod should be about 1/8" (3 mm) larger in diameter than the width of the joint to allow for compression. Soft backer rod should be approximately 25% larger in diameter than the joint width. The sealant does not adhere to it, and no separate bond breaker is required. Do not prime or puncture the backer rod.

#### SURFACE PREPARATION

Substrates must be structurally sound, fully cured, dry and clean. Substrates should always be free of the following: dirt, loose particles, oil, grease, asphalt, tar, paint, wax, rust, waterproofing or curing and parting compounds, membrane materials and sealant residue.

**AAMA 714-15 Voluntary Specification for Liquid Applied Flashing Used to Create a Water-Resistive Seal Around Exterior Openings in Buildings**

PROPERTY	RESULTS	TEST METHOD
<b>Peel Adhesion</b> Control AAMA 714 Sec 5.1 UV exposure Sec 5.3 ASTM G154 Elevated temperature AAMA 714 Sec 5.4 Thermal cycling AAMA 714 Sec 5.5 7 day water immersion AAMA 714 Sec 5.7	Tested over concrete (mortar), CMU, plywood, aluminum at 12 mils thickness Pass control and after conditioning, min. 5 pli	AAMA 714 Sec 5.1, ASTM C794-18
<b>Nail Sealability</b>	Pass, before and after thermal cycling, 24 hours at 40 °F with 31.75 mm (1 1/4") head of water.	AAMA 714 Sec 5.2 (AAMA 711 Sec 5.2), ASTM D1970-13
<b>Accelerated Aging</b>	Pass, no deleterious effects such as wrinkling, distortion, blistering, expansion, shrinkage or warpage after 21 days (504 hours) to Cycle 1 of ASTM G155.	AAMA 714 Sec 5.3, ASTM G155
<b>Elevated Temperature</b>	Pass, no deleterious effects such as wrinkling, distortion, blistering, expansion, shrinkage or warpage at 50 °C (122 °F), 65 °C (149 °F), and 80 °C (176 °F)	AAMA 714 Sec 5.4
<b>Thermal Cycling</b>	Pass, no deleterious effects such as wrinkling, distortion, blistering, expansion, shrinkage or warpage at 10 cycles	AAMA 714 Sec 5.5
<b>Crack Bridging</b>	Pass, no failure after 10 cycles with 1/8" gap and water holdout of 550 mm (21.7") for 24 hours.	AAMA 714 Sec 5.6, ASTM C1305
<b>Water Immersion</b>	Pass, no deleterious effects such as wrinkling, distortion, blistering, expansion, shrinkage or warpage after 7 days	AAMA 714 Sec 5.7
<b>Adhesion to Damp Substrates</b>	Pass, min 5 pli, over mortar	AAMA 714 Sec 6.1 and 6.2
<b>Water Vapor Permeability</b>	5.8 perms @ 20 mils 5.4 perms @ 30 mils	AAMA 714 Sec 6.3, ASTM E96 Method B

Note: All testing with MasterSeal® NP 150 at 20 mils unless otherwise noted

TABLE 1  
Joint Width and Sealant Depth

JOINT WIDTH, IN (MM)	SEALANT DEPTH AT MIDPOINT, IN (MM)
1/2–3/4 (13–19)	1/4–3/8 (6–10)
3/4–1 (19–25)	3/8–1/2 (10–13)
1–1 1/2 (25–38)	1/2 (13)

Yield  
LINEAR FEET PER GALLON\*

JOINT DEPTH, (INCHES)	JOINT WIDTH (INCHES)								
	1/2	5/8	3/4	7/8	1	1 1/2	2	3	
1/4	154	122	–	–	–	–	–	–	
3/8	–	82	68	58	51	–	–	–	
1/2	–	–	51	44	38	26	19	12	

METERS PER LITER

JOINT DEPTH, (MM)	JOINT WIDTH (MM)							
	13	16	19	22	25	38	50	75
6	12.4	9.8	–	–	–	–	–	–
10	–	6.6	5.5	4.7	4.1	–	–	–
13	–	–	4.1	3.5	3.0	2.2	1.5	0.7

#### EIFS

1. MasterSeal NP 150 should be applied to the system base coat for best adhesion and to avoid delamination of EIFS finish applied in the joint.
2. Base coat must be sound, well bonded, properly cured and of sufficient depth to comply with manufacturer's specifications.
3. Certain EIFS systems require the use of a primer. Refer to the EIFS manufacturer for recommendations.

**CONCRETE, STONE, AND OTHER MASONRY**  
Clean by grinding, sandblasting or wire brushing to expose a sound surface free of contamination and laitance.

#### WOOD

New and weathered wood must be clean, dry and sound. Scrape away loose paint to bare wood. Any coatings on wood must be tested to verify adhesion of sealant or to determine an appropriate primer.

#### METAL

Remove scale, rust and loose coatings from metal to expose a bright white surface. Any coatings on metal must be tested to verify adhesion of sealant or to determine an appropriate primer.

#### PRIMING

1. MasterSeal NP 150 is generally a non-priming sealant, but special circumstances or substrates may require a primer.
  - Porous materials subject to intermittent water immersion require priming. Use MasterSeal P 179.
  - Certain architectural metal finishes may require priming with MasterSeal P 173.
  - It is the user's responsibility to check the adhesion of the cured sealant on typical test joints at the project site before and during application. Refer to the technical data guides for MasterSeal P 179 and MasterSeal P 173.
  - For green concrete applications, MasterSeal P 173 or MasterSeal P 179 must be used.
2. Apply primer full strength with a brush or clean cloth. A light, uniform coating is sufficient for most surfaces. Very porous surfaces may require a second coat of MasterSeal P 179; however, do not over apply.
3. Allow primer to dry before applying MasterSeal NP 150. Depending on temperature and humidity, primer will be tack-free in 15–30 minutes. Priming and sealing must be done on the same day.

#### APPLICATION

1. MasterSeal NP 150 comes ready to use. Apply using professional grade caulking gun. Do not open cartridges, ProPaks or pails until preparatory work has been completed.
2. Fill joints from the deepest point to the surface by holding an appropriately sized nozzle against the back of the joint.
3. Dry tooling is recommended. Proper tooling results in the correct bead shape, neat joints, and optimal adhesion.
4. MasterSeal NP 150 can be applied below freezing temperatures down to 10 °F only if substrates are completely dry, free of moisture and clean. Contact Technical Service for more information.

#### FLASHING ROUGH OPENINGS APPLICATION:

1. Apply a bead of MasterSeal NP 150 in each corner of the rough opening, ensuring that the corners are fully sealed.
2. Apply additional MasterSeal NP 150 in a zigzag pattern onto the head, sill, jambs and exterior substrate.
3. Spread MasterSeal NP 150 evenly across the rough opening to form a continuous, void and pinhole-free membrane with a 20 mil thickness.
4. Extend MasterSeal NP 150 membrane a minimum of 4 inches onto the exterior wall, maintaining 20 mil thickness.
5. Allow MasterSeal NP 150 to cure prior to the installation of windows, doors and other assemblies.

---

#### CURING TIME

The cure of MasterSeal NP150 varies with temperature and humidity. The following times assume 75 °F (24 °C), 50% relative humidity, and a joint ½" width by ¼" depth (13 by 6 mm).  
–Skins: 60–90 minutes  
–Full cure: approximately 1 week  
–Immersion service: 21 days

---

#### CLEAN UP

1. Immediately after use, clean equipment with MasterSeal 990 or xylene. Use proper precautions when handling solvents.
2. Remove cured sealant by cutting with a sharp-edged tool.
3. Remove thin films by abrading.

---

#### FOR BEST PERFORMANCE

- In cold weather, store container at room temperature for at least 24 hours before using.
- Not for use in glazing applications. Do not apply on glass and plastic glazing panels.

- For proper sealing of joint edges, all window covers must be removed prior to application of sealant.
- Do not allow uncured MasterSeal NP 150 to come into contact with alcohol-based materials or solvents.
- MasterSeal NP 150 should not be applied adjacent to other uncured sealants and certain petroleum based products.
- MasterSeal NP 150 can adhere to other residual sealants in restoration applications. For best results, always clean the joint as advised in the Surface Preparation section of this data guide. A product field adhesion test for MasterSeal NP 150 within the specific application is always recommended to confirm adhesion and suitability of the application.
- MasterSeal NP 150 should not be used for continuous immersion in water. Contact Technical Service for recommendations.
- Do not apply over freshly treated wood. Allow six months for weathering.
- Do not use MasterSeal P 179 on nonporous surfaces such as aluminum, steel, vinyl or Kynar 500 based paints. Use MasterSeal P 173 on coated metals when testing dictates.
- Lower temperatures and humidity will extend curing times.
- MasterSeal NP 150 can be painted over after a thin film or skin forms on the surface.
- In green concrete applications, sealing joints in concrete prior to 72 hours after concrete placement will impact the ability of sealant to gain adhesion. MasterSeal P 179/P 173 should be used as a primer in green concrete applications. It is always recommended to conduct a mock up when applying NP 150 to green concrete.
- For low surface energy substrates, MasterSeal P 173 and field adhesion testing are recommended.
- Pursuant to accepted industry standards and practices, using rigid paints and/or coatings over flexible sealants can result in a loss of adhesion of the applied paint and/or coating, due to the potential movement of the sealant. However, should painting and/or coating be desired it is required that the applicator of the paint and/or coating conduct on-site testing to determine compatibility and adhesion.
- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

---

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [master-builders-solutions.com/en-us](http://master-builders-solutions.com/en-us), e-mailing your request to [mbsbscst@mbcc-group.com](mailto:mbsbscst@mbcc-group.com) or calling 1(800)433-9517. Use only as directed.

**IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.**

---

#### LIMITED WARRANTY NOTICE

Master Builders Solutions warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information

and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.