

TECHNICAL DATA SHEET

AV-202® MULTIGROUT

HYDROPHILIC POLYURETHANE GROUT

DESCRIPTION

AV-202® Multigrout is a single component, moisture-activated MDI/TDI blended polyurethane injection resin designed for sealing active water leaks in large cracks or joints in concrete structures. **AV-202** reacts with moisture and is versatile in that it cures tough and impermeable with superb adhesive qualities at a 1:1 water to resin ratio, or gel at a 10:1 water to resin ratio.

APPLICATIONS

- Large cracks or joints in concrete, or used in conjunction with **AV-215 Resin Rod™** or **AV-219 Fibrotite™** (Oakum)
- Designed for applications where high-volume water flow is an active and/or potential problem and a high viscosity chemistry is required
- Used successfully in manhole sealing and pipe penetrations
- Excellent choice for moving cracks and joints

FEATURES AND BENEFITS

- **NSF/ANSI/CAN 61 Drinking Water Systems Component Certified**
- 100% solids
- Free rise expands 400% – 600%
- Solvent-free and non-corrosive
- Cures flexible with superb adhesive properties
- Can accept up to 10X its volume in water
- May be used in underwater applications

GROUTING TECHNIQUES

- Expanded Gasket Placement Technique (EGP)
- Variable Pressure Application Technique (V-PAT) – Crack Injection

HOW IT WORKS

AV-202 can be applied via two techniques: EGP or V-PAT. The resin reacts to moisture to form a resilient, flexible seal accomplished by three mechanisms: the resin seeks out water in the space and *adheres* to the surface, then begins to expand forming a tight compressive seal, while the network of compressed grout material within all the cracks forms a mechanical lock. Gently shake or stir container(s) before using.

RATIOS

The preferred ratio is 1:1 (water to resin), however it is effective up to a ratio of 10:1 with water. Pumped as a single component; no pre-mixing required.

PACKAGING

Product is packaged by weight based on specific gravity.

Net Wt.

Drum	484 lbs. (220 kg)
Pail	44 lbs. (20 kg)
Gallon	8 lbs. (3.6 kg)
Cartridge	~10.1 fl. oz. (~ 300 ml)

SHIPPING

- Motor class 55
- Non-hazardous
- Air freight available

CLEANING PRODUCTS

- **AV-208** Technical Grade Acetone™ (CAS# 67-64-1) – removes moisture from equipment (see Performance section)
- **AV-222** Cleaner™ (Proprietary Blend) – removes cured resin from equipment
- **AV-284** Pump Wash™ (Proprietary Blend) – removes uncured resin from pump hose

PROPERTIES*

UNCURED

Appearance:	Brown resin
Viscosity:	3,200 – 6,000 cP @ 77°F (25°C)
Flash Point:	253.4°F (123°C)
Specific Gravity:	1.090 @ 72°F (22°C) ± 3%
Density:	9.09 lbs. per gallon ± 3% (1.090 kg/L ± 3%)

CURED

Appearance:	Milky colored, flexible
Tensile Strength:	TBD
Elongation:	TBD

*Laboratory Results

PERFORMANCE

Flush equipment with **AV-208** Technical Grade Acetone™ before and after use to remove moisture and clean equipment. For best results, use between 60°F – 90°F (16°C – 32°C). Performance will be influenced by site conditions. If site temperatures are low, use a heat source to warm to ~72°F (22°C) and apply. Do not use open flame as a heat source. At temperatures of 45°F (7°C), the viscosity of the product can significantly increase, making the miscibility with the reaction water more difficult.

STORAGE

Store in temperatures within or near 45°F – 95°F (7°C – 35°C) in a dry atmosphere. Keep container tightly closed when not in use. Packaged under dry nitrogen to keep moisture out and extend shelf life.

Note: storage of opened/partial containers at the lower range of the recommended storage temperature is not advised. The moisture in the air of the head space above a partial container might condensate and causes the grout to premature gel in the container.

SAFETY

Always use OSHA-approved personal protective equipment (PPE). Refer to the SDS for complete safety precautions. The SDS is available by request or via download at avantigrout.com.

NOTICE

The data, information and statements contained herein are believed to be reliable but are not construed as a warranty or representation for which Avanti International assumes any legal responsibility. Since field conditions vary widely, users must undertake sufficient verification and testing to determine the suitability of any product or process mentioned in this or any other written material from Avanti for their own particular use. **NO WARRANTY OF SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS MADE.** In no case shall Avanti International be liable for consequential, special, or indirect damages resulting from the use or handling of this product.



AV-202® Multigrout is tested and certified by WQA against NSF/ANSI/CAN 61 Drinking Water System Components

For product use restrictions visit www.wqa.org



AVANTI

Stop leaks. Stabilize soil.
Control groundwater. **Permanently.**

Rev. 10.2022

TECHNICAL DATA SHEET

AV-202[®] MULTIGROUT

HYDROPHILIC POLYURETHANE GROUT